

ARBO

ARBOSIL 1090

ARBOSIL 1090

Arbosil 1090 is a one part Low Modulus Neutral Cure Silicone Sealant which cures on exposure to moisture vapour to form a very elastic silicone rubber. Arbosil 1090 has good adhesion to concrete, brickwork, metals and many other common construction substrates.

MAIN APPLICATIONS

Recommended for use in many construction applications including curtain walling, both original and remedial perimeter sealing, structural joints in light cladding, profiled metal roof sheets, joints in flat roof systems and guttering joints.

NB: Not recommended for overpainting, use with laminated glass and use against natural stone.

APPLICATION INSTRUCTIONS

Joint Preparation

The joint surfaces must be clean, dry and free from all contamination. The surfaces should be degreased using the appropriate Arbo Cleaner. Primers may be required on some substrates. It is recommended that Adsheed Ratcliffe Technical Services Department should be consulted and advice obtained with regard to the choice of primer for specific purposes.

Joint Backing

Where applicable, appropriate joint filler e.g. closed cell polyethylene foam, should be used to provide the correct joint depth.

Application

All joint preparation, priming, and sealant application should be carried out in accordance with BS 8000 Part 16, the British Standard for the sealing of joints in buildings using sealants. Arbosil 1090 is supplied in polyethylene 380ml cartridges and can be applied into the joint using an Arbo Caulking Gun.

TECHNICAL DATA

Colours	Grey, Black, Buff, Dark Bronze, Portland, Rustic Red*.
Skin Time at 20° C/65 % RH:	10 - 20 minutes
Application Temperature:	+ 5° C to + 50° C
Service Temperature:	- 50° C to + 120° C
Cure Rate at 20° C/65 % RH:	1mm/24 hours
Chemical Resistance:	Resistant to most dilute acids and alkalis. Organic solvents may cause the sealant to swell and lose adhesion
UV Resistance:	Very Good
Service Life:	25 years +
Movement Accommodation:	Butt joints (movement in tension and compression): 70 %. Do not exceed \pm 50 % in any one direction Lap joints (movement in shear): 150 %. Do not exceed \pm 100 % in any one direction

*[Special colours can be made to order subject to minimum batch size quantities. Please contact Adshead Ratcliffe Technical Services Department for further information].

JOINT SIZE SUITABILITY**Joint width**

Minimum 6mm

Maximum 25mm (single application); for advice on multiple applications please contact Adshead Ratcliffe Technical Services Department.

Joint Depth

Minimum 10mm on porous substrates

Minimum 6mm on non-porous substrates

Maximum 20mm

Width: Depth ratio (within above min/max restrictions)

2:1 butt joints

1:1 lap joints

HEALTH AND SAFETY

No particular hazards with this product but please consult Material Safety Data Sheet for full information.

PACKAGING

25 x 380ml Polyethylene Cartridges per box.

Polyethylene Nozzles are included in each box.

ACCESSORIES

Primers

Arbo Primer 2650 (500ml tin) Yield approximately 125 metres per tin
 Arbo Primer 2172 (500ml tin) Yield approximately 200 metres per tin

Cleaners

Arbo Cleaner No.17- 1 Litre Tin
 (Xylene based – not suitable for use with plastics or delicate finishes)
 Arbo Cleaner No. 16 - 1 Litre Tin
 (Alcohol Based)

Ancillary Equipment

Polyethylene Nozzles
 Arbo Caulking Guns

QUANTITY ESTIMATOR

Joint Size (mm)	Metres/Litre
6 x 6	27.8
9 x 6	18.5
12 x 9	9.3
18 x 10	5.6
25 x 10	4.0

SPECIFICATION COMPLIANCE

BS EN ISO 11600 – F/G – 25 LM

IMPORTANT: The information in this leaflet is given in good faith and based on results gained from experience and tests. However, all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control. Goods are supplied subject to the Company's terms and conditions of sales, a copy of which is available on request.



CARLISLE® Adshead Ratcliffe & Co. Ltd United Kingdom

Derby Road | Belper
 Derbyshire

DE56 1WJ
 United Kingdom

T +44 (0)1773 826661
 F +44 (0)1773 821215

E customerservice.arbo@ccm-europe.com
www.arbo.co.uk