

ARBOOTHANE 1245

Arbothane 1245 is a one part Polyurethane Sealant which cures on exposure to moisture vapour to form a tough but flexible rubber. Arbothane 1245 has good adhesion to concrete and many common construction substrates.

MAIN APPLICATIONS

Recommended for use in floor joints, expansion joints and structural cladding applications.

NB: Not recommended for use against natural stone.

APPLICATION INSTRUCTIONS

Joint Preparation

The joint surfaces must be clean, dry and free from all contamination. The surfaces should be degreased using the appropriate Arbo Cleaner. Primers may be required on some substrates. It is recommended that Adshead Ratcliffe Technical Services Department should be consulted and advice obtained with regard to the choice of primer for specific purposes.

Joint Backing

Where applicable, appropriate joint filler e.g. closed cell polyethylene foam, should be used to provide the correct joint depth.

Application

All joint preparation, priming, and sealant application should be carried out in accordance with BS 8000 Part 16, the British Standard for the sealing of joints in buildings using sealants. Arbothane 1245 is supplied in 600ml foil packs and can be applied into the joint using an Arbo Foil Pack Gun.



TECHNICAL DATA

Colours	Grey
Skin Time at 20° C/65 % RH:	90 minutes
Application Temperature:	+ 5° C to + 40° C
Service Temperature:	- 30° C to + 110° C
Typical Shore A Hardness:	45
Cure Rate at 20° C/65 % RH:	2mm/24 hours
Chemical Resistance:	Moderate resistance to most dilute acids and alkalis. Organic solvents may cause the sealant to swell and lose adhesion.
UV Resistance:	Very Good
Service Life:	15 years +
Movement Accommodation:	Butt joints (movement in tension and compression): 35 %.
Lap joints (movement in shear):	70 %

JOINT SIZE SUITABILITY

Joint Width

Minimum 6mm

Maximum 25mm (single application); for advice on multiple applications please contact Adshead Ratcliffe Technical Services Department.

Joint Depth

Minimum 10mm on porous substrates

Minimum 6mm on non-porous substrates

Maximum 20mm

Width: Depth ratio

(within above min/max restrictions)

2:1 butt joints

1:1 lap joints

STORAGE LIFE

12 months in original unopened packaging stored in a cool, dry place out of direct sunlight.

HEALTH & SAFETY

Contains Isocyanates. Please consult Material Safety Data Sheet for full information.

PACKAGING

20 x 600ml Foils per box. Polyethylene Nozzles are included in each box.

CARLISLE® Adshead Ratcliffe & Co Ltd. United Kingdom

Derby Road | Belper
Derbyshire

DE56 1WJ
United Kingdom

T +44 (0)1773 826661
F +44 (0)1773 821215

E customerservice.arbo@ccm-europe.com
www.arbo.co.uk

ACCESSORIES

Primers

Arbokol AG2 Porous Primer (500ml tin). Yield approximately 125 metres per tin

Arbo Primer 7750 (500ml tin). Yield approximately 200 metres per tin

Cleaners

Arbo Cleaner No.17- 1 Litre Tin
(Xylene based – not suitable for use with plastics ordelicate finishes)

Arbo Cleaner No. 16 - 1 Litre Tin
(Alcohol Based)

Equipment

Arbo Foil Pack Gun

SPECIFICATION COMPLIANCE

BS EN ISO 11600 – F – 25 HM

**UK
CA**

QUANTITY ESTIMATOR

JOINT SIZE (MM)	METRES/LITRE
6 x 6	27.8
9 x 6	18.5
12 x 9	9.3
18 x 10	5.6
25 x 10	4.0

IMPORTANT: The information in this leaflet is given in good faith and based on results gained from experience and tests. However, all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control. Goods are supplied subject to the Company's terms and conditions of sales, a copy of which is available on request.

CARLISLE® Adshead Ratcliffe & Co Ltd. United Kingdom

Derby Road | Belper
Derbyshire

DE56 1WJ
United Kingdom

T +44 (0)1773 826661
F +44 (0)1773 821215

E customerservice.arbo@ccm-europe.com
www.arbo.co.uk