

ARBO Seal Pro[®]

ARBOKOL 1025 SP

Arbokol 1025 SP is a unique two-part Epoxy sealant which cures to form a hard-wearing seal, designed to accommodate small amounts of movement in extension but considerable movement in compression.

Recommended for use in a variety of internal stress relief joint systems where continual water resistance and a high degree of chemical resistance (especially to common cleaning substances) are required.

Main Applications

Swimming pools, compression joints, tile to tile joints (no primer required), long term water immersed joints, shower rooms.

NB. Not recommended for structural movement joints.

Application Instructions

Joint Preparation

The joint surfaces must be clean, dry and free from all contamination. Surfaces should be degreased using the appropriate surface cleaner (contact ARBO[®] Technical Services for further information).

Note: Product must only be applied to dry surfaces and allowed to fully cure before any form of immersion.



A part of

CARLISLE
CM EUROPE

ARBOKOL 1025 SP

Mixing

The ratio of base to curing agent controls the performance properties of Arbokol 1025 SP and tins are filled off to an exact mixing ratio. It is vital therefore that the whole contents of the curing agent tin are added to the base tin. The 2 components must be thoroughly mixed to ensure complete homogeneity (Spiral "pig tail" mixing equipment is recommended).

Application

The usual application method once mixed is to fill the sealant into empty cartridge dispensers using a follower plate. The cartridge is placed over the hole in the centre of the plate and filled by applying steady downward pressure. Insert the plunger into the cartridge and the mixed sealant is then ready for application using an ARBO Caulking Gun. The sealant should be extruded firmly into the joint by maintaining an even pressure on the trigger of the gun.

Joint Backing

Where applicable, use appropriately sized closed cell, cross-linked polyethylene foam.

All joint preparation and sealant application should be carried out in accordance with BS8000-16:1997 + A1:2010 (British standard for the sealing of joints in buildings using sealants).

Joint Size Suitability

Joint width

Minimum 6mm.
Maximum 20mm (single application).

Joint depth

Minimum 10mm on porous substrates.
Minimum 6mm on non-porous substrates.
Maximum 10mm.

Width: Depth ratio
Contact ARBO Technical Service Department

Health and Safety

The base component is polyamide based and the curing agent component contains epoxy resin. Both components require careful handling. Please consult the Safety Data Sheet for each component before use.

Packaging

1.2 Litre Set, with separate tins for Base and Curing Agent. Follower plate.

Accessories

Cleaners

ARBO Cleaner 17 - 1 litre tin.
(Xylene based – not suitable for use with plastics or delicate finishes)
ARBO Cleaner 16 – 1 Litre tin
(Alcohol Based)

Equipment

Spiral Mixing Paddle
Empty Cartridges, Nozzles and Plungers

Ancillary Equipment

Polyethylene nozzles
ARBO caulking guns

Technical Data

Application Temperature:	+ 10° C to + 40° C
Service Temperature:	- 20° C to + 90° C
Typical Shore D Hardness (cured at 20° C):	50-70
Work Life (Typical at 20° C):	60- 90 minutes
Cure Rate at 20° C:	48 hours. At lower temperatures cure rate will be extended.
Chemical Resistance:	Resistant to most cleaning chemicals used in swimming pool situations (neat Hypochlorite crystals should not be applied to 1025 SP).
Movement Accommodation:	Tension: 5 %. Compression: 50 %
Colours	Off White, Grey

Quantity Estimator

Joint Size (mm)	Metre/1.2 Litre Set
6 x 6	33.3
9 x 6	23
12 x 9	11
20 x 10	6

Important: The information in this leaflet is given in good faith and based on results gained from experience and tests. However, all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control. It is the user and specifier's responsibility to ensure ARBO product is suitable for the intended use: consult ARBO Technical Services for specific advice. Goods are supplied subject to the Company's terms and conditions of sales, a copy of which is available on request.



CARLISLE® Adsheed Ratcliffe & Co. Ltd

United Kingdom
Derby Road | Belper

Derbyshire
DE56 1WJ

T +44 (0)1773 826661

E info.arbo@ccm-europe.com
www.arbo.co.uk

CARLISLE
CM EUROPE