

ARBO Bond Pro[®]

ARBOMERIC MP20

Arbomeric MP20 is a one-part high modulus modified polymer sealant which cures on exposure to moisture vapour to form a tough but elastic rubber.

Main Applications

Arbomeric MP20 is recommended for use in many forms of construction including: structural joints in heavy cladding, structural movement joints in floors and floor joints in heavily trafficked areas, prisons and secure units (supervised areas) forming anti-pick/anti-vandalism joints, or any area that could be subject to abuse and vandal attack.

NB: Not recommended for joints in lightweight cladding and swimming pools. Products over-paintable once fully cured; pre-use tests are advised to demonstrate compatibility with individual paints.

Application Instructions

Joint Preparation

The joint surfaces must be clean, dry and free from all contamination. The surfaces should be degreased using the appropriate ARBO[®] Cleaner. ARBO Primer 2650 is recommended on porous materials such as concrete and stone. It is recommended that ARBO Technical Services be consulted regarding the use of ARBO primer for specific purposes.

Joint Backing

Where applicable, use appropriately sized closed cell, cross-linked Polyethylene foam. All joint preparation, priming, and sealant application should be carried out in accordance with BS 8000-16:1997+A1 2010 the British Standard for the sealing of joints in buildings using sealants.



A part of

ARBOMERIC MP20

Application

Arbomeric MP20 is supplied in polyethylene 380ml cartridges and 600ml foils.

Joint Size Suitability

Joint width

Minimum 6mm
Maximum 25mm

Joint depth

Minimum 10mm on porous substrates.
(12mm in floor joints)
Minimum 6mm on non-porous substrates. (12mm in floor joints)
Maximum 20mm.

Width: Depth ratio (within above min/max restrictions).

2:1 butt joints
1:1 lap joints/floor joints

Health and Safety

Please consult the Safety Data Sheet for full information.

Storage Life

12 months in original unopened packaging stored in a cool, dry place out of direct sunlight.

Packaging

25 x 380ml Polyethylene Cartridges per box. Polyethylene Nozzles are included in each box.

Accessories

Primers

ARBO Primer 2650 (500ml tin)
Yield approximately 125 metres per tin.

Cleaners

ARBO Cleaner No.17-1 Litre Tin (Xylene based – not suitable for use with plastics or delicate finishes).
ARBO Cleaner No. 16-1 Litre Tin (Alcohol Based).

Ancillary Equipment

Polyethylene Nozzles
ARBO Caulking Guns

Technical Data

Skin Time at 20° C/65 % RH:	20-30 minutes
Application Temperature:	+ 5° C to + 35° C
Service Temperature:	- 40° C to + 120° C
Chemical Resistance:	Resistant to most dilute acids and alkalis. Organic solvents may cause the sealant to swell and lose adhesion. Strong cleaning agents can cause surface deterioration and may affect the efficiency of the material.
UV Resistance:	Very good
Service Life:	20 years + (when used in trafficked areas the life may be reduced)
Movement Accommodation:	Butt joints (movement in tension and compression): 35 %. Lap joints (movement in shear):
Colours	White, Grey, Black
Modulus @ 100 % Extension:	1.0 - 1.12 N/mm ²
Ultimate Elongation:	220%
Tensile Strength @ Break:	1.3-1.6 N/mm ²
Typical Shore Hardness	40 - 45

Specification Compliance

BS EN ISO 11600 – F – 20 HM

Important: The information in this leaflet is given in good faith and based on results gained from experience and tests. However, all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control. It is the user and specifier's responsibility to ensure ARBO product is suitable for the intended use: consult ARBO Technical Services for specific advice. Goods are supplied subject to the Company's terms and conditions of sales, a copy of which is available on request.



CARLISLE® Adsheed Ratcliffe & Co. Ltd

United Kingdom
Derby Road | Belper

Derbyshire
DE56 1WJ

T +44 (0)1773 826661

E info.arbo@ccm-europe.com
www.arbo.co.uk

CARLISLE
CM EUROPE